

Testing Report

 KFPI Korea Flame Proof Institute 5F, 7, Nonhyeon-ro, Seocho-gu, Seoul, Korea Tel : 02 556 1919 Fax : 02 556 1331 http://www.kfpi.kr	Certificate No. KFPI — 24 — 01498 Page (1) / Pages (2)	
---	---	---

1. Client

Name : SAMSUNG INTERIOR FILM Co., Ltd.
Address : 215-35, Yeongil-ro, Yeongjung-myeon, Pocheon-si, Gyeonggi-do, Republic of Korea / 031-534-8100
Date of Receipt : February. 20. 2024.

2. Use of Report : Submit to the company

3. Test Sample Name / Quantity

Brand : SAMSUNG INTERIOR FILM Co., Ltd.
Address : 215-35, Yeongil-ro, Yeongjung-myeon, Pocheon-si, Gyeonggi-do, Republic of Korea
Sample Name : SOIF SAMSUNG INTERIOR FILM (Fire Retardant)
Quantity : 3 EA

4. Date of Test : February. 23. 2024.

5. Testing Site : KFPI, 5F, 7 Nonhyeon-ro, Seocho-gu, Seoul, Korea


6. Test Method Used : National Fire Agency Notice Part No. 2022-29 Article 6

7. Test Result

Experiment	Standards	Experiment Results			Remark
		1	2	3	
Carbonization Size	30 cm ²	21.5 cm ²	20.5 cm ²	21.0 cm ²	
Carbonization Length	20 cm	6.6 cm	6.5 cm	6.4 cm	
After Flame Time	03 s	0.0 s	0.0 s	0.0 s	
After Glow Time	05 s	0.0 s	0.0 s	0.0 s	





The results shown in this test report refer only to the sample(s) tested unless otherwise stated.

This test Report cannot be reproduced, except in full.

Affirmation	Tested by Name: HyungSeok Jin 	Technical Manager Name: GooJong Roh 
-------------	--	--

FEBRUARY. 28. 2024.

Korea Flame Proof Institute



Testing Report



Korea Flame Proof Institute

5F, 7, Nonhyeon-ro, Seocho-gu, Seoul, Korea

Tel : 02 556 1919 Fax : 02 556 1331



<http://www.kfpi.kr>

Certificate No. KFPI — 24 — 01498

Page (2) / Pages (2)



※ Pictures of Sample



— END —

